

DECLARATION



I, the undersigned: J.C. Volmer

sworn Dutch and European Patent Attorney of:

EP&C
295A, Sir Winston Churchilllaan
Rijswijk, The Netherlands,

hereby declare:

- that I am conversant in the Dutch and English languages;
- that the attached 17 pages contain a true and faithful translation – made at the best of my ability

Netherlands Patent Application No. 1025774

Filed March 19, 2004

relating to:

“ Method for producing a base material for screen printing, and base material of this type”.

done at Rijswijk, August 20, 2010

A handwritten signature in black ink, appearing to be 'J.C. Volmer', written over a horizontal line.

J.C. Volmer

Method for producing a base material for screen printing, and
base material of this type

- 5 The invention relates to a method for producing a base material
for screen printing, which comprises a screen, a resist layer
comprising photosensitive material and a protective film.

A base material for screen printing which comprises a screen, a
10 resist layer comprising photosensitive material and a protective
film, is known per se and available from Gallus Ferd. Rüschi AG,
under the trade name Screeny Siebdruckplatten. In the specialist
field, the screen is also described as a network of dykes which
delimit openings. The known screen comprises a woven metal mesh
15 galvanized with nickel. The resist layer of photosensitive
material is known in the art. When the base material is used for
screen printing, first of all the protective film is removed
from the base material. The resist layer is exposed according to
a defined pattern, developed and the resist layer is cured in
20 accordance with said pattern. After the unexposed, uncured
resist layer has been removed, the base material can function as
a stencil during the screen printing. There are also known
resist layers which react in the opposite way to exposure, i.e.
which cure without exposure and do not cure if they are exposed.
25 Therefore, the negative image of the pattern exposed is cured.
The protective film has the function of protecting the resist
layer during storage, transportation and when the base material
is being rolled up and unrolled. In addition, the film provides
the base material with an attractive appearance. The base
30 material can, for example, be made into a cylindrical shape and
used in this form for screen printing, in which case - after the
protective film has been removed and after the resist layer has
been exposed and developed - the ink is guided through the
screen using a squeegee. The pattern which is printed in the
35 process is determined by the resist layer which is present on
and in the screen.

It has now been found that the extent to which the surface of the resist layer is flat on the side of the protective film leaves something to be desired: the surface of the resist layer is visible in the form of a more or less undulating surface, also referred to as a relief. When the base material is used for screen printing, this relief has proven to have an adverse effect on the results of printing, since the printed image is less sharp at locations where the relief is prominent.

10 It is an object of the present invention to completely or at least partially resolve the above problems by means of a novel method for producing the base material, producing a base material with less relief.

15 The invention further relates to a base material having less relief.

According to a first aspect, to this end the invention of the type as described in the preamble, comprises the steps of:

- 20 a) applying a first resist layer to one side of the protective film,
- b) drying the first resist layer,
- c) applying an additional resist layer to the first resist layer, and
- 25 d) then applying a screen to the additional resist layer, the side of the additional resist layer to which the screen is applied being wet, and the resist layer comprising an additional resist layer and a first resist layer.

30 The method according to the invention has the advantage that it produces a base material whereof the surface of the resist layer has an improved smoothness, i.e. a reduced relief, on the side of the film. The relief - also referred to as the roughness - of the surface of layers is expressed by a Rz value, which is
35 measured in accordance with the DIN 4768 standard. The method according to the invention makes it possible to reduce the relief of the surface of the resist layer on the film side to such an extent that the Rz value is less than 15 micrometres,

preferably less than 5 micrometres, most preferably 1-2 micrometres. According to the method of the invention, this reduction is achieved by the resist layer being built up in at least two steps, in such a manner that the screen is applied to
5 a wet side of the additional resist layer that has previously been applied.

The application of the resist layer to the protective film can be carried out in various ways which are known in the specialist
10 field, for example using a patterned roller, a squeegee, doctor, stencil or screen, and also by the processes known as slot coating, slide coating and knife and roll coating (cf. "*Liquid film coating*" by S.F. Kistler and P.M. Schweizer, Chapman & Hall, London, 1997). The first and/or additional resist layers
15 can be applied in various steps, i.e. the first and additional resist layers may be composed of different resist sublayers. It is preferable for the first resist layer to be applied in one step and then the additional resist layer to be applied in one step. The first resist layer is preferably dried at a
20 temperature which is lower than the curing temperature of the resist layer. This means that the drying step b) does not, in a later stage of use of the base material, influence the exposure of the resist layer with a pattern corresponding to the image that is to be printed. A suitable drying temperature is selected
25 as a function of the resist used, for example a temperature of lower than 100°C, and preferably around 50°C, for a water-based resist with a water content of 55%. As an alternative, the drying of the first resist layer can take place at a temperature which is equal to or higher than the curing temperature of the
30 resist layer, provided that the drying is carried out for a very short period of time, so that curing of the first resist layer does not yet occur. The feature that the side of the additional resist layer to which the screen is applied is "wet", is to be understood as meaning that the resist has a viscous character,
35 with the result that during the application of the screen to the additional resist layer, the resist can be deformed and/or can flow into the openings between the dykes of the screen. Besides, it should be noted that during step c) the additional resist

layer influences the dry character of the first resist layer, with the result that the first resist layer also becomes wet to a certain extent in the region where it adjoins the additional resist layer.

5

The screen reaches a certain depth in the resist layer depending on the viscosity of the resist layer and way in which the screen is applied to the resist layer. In this case, the screen can penetrate not only into the additional resist layer but also
10 into the first resist layer. In general, the depth which the screen reaches in the resist layer is limited by the position where the resist in the resist layer is dry or where the viscosity of the resist in the resist layer has become too high. In this case, the thickness of the dried first resist layer can
15 determine the depth reached by the screen in the resist layer as a whole. For the sake of completeness, it should be noted that the application of the screen to the resist layer according to the invention implies an adhesion between screen and resist layer.

20

There are various suitable types of screen for the base material, such as an optionally galvanized woven plastic fabric, a woven metal mesh, a galvanized knitted fabric or woven fabric of plastic threads or metal wires, and screens formed by
25 electroforming. It is preferable for the screen to have a mesh number of 70 to 500. The openings in the screen are, for example, round, orthogonal or hexagonal.

For the sake of completeness, it should be noted that the resist
30 layer as a whole is dried before the base material is stored or exposed for further use.

In the method according to the invention, it is preferable for the screen to be applied without the additional resist layer
35 being dried beforehand. This creates a rapid and simple method for carrying out the method according to the invention.

As an alternative, the additional resist layer is dried

beforehand, for example for the purpose of storage, and is moistened at any subsequent time.

Further preferably, in the method according to the invention a
5 screen which is an electroformed screen is applied. An
electroformed screen is formed by growing a metal skeleton by
any galvanic method on a network of conductive tracks of a die.
The conductive tracks, which delimit insulating regions,
correspond to the dykes of the skeleton, which dykes delimit
10 openings corresponding to the insulating regions. In general,
after the die has been removed, the skeleton is grown further,
in a secondary step, by the application of a metal layer in an
electroplating bath. An electroformed screen itself has a
surface - referred to in the description of figures below as a
15 contact surface - which is highly planar, since in
electroforming technology the screen is grown uniformly onto a
flat die, with the dykes having an even, i.e. uniform,
thickness. A woven fabric, by contrast, inherently has a varying
thickness on account of the warp and weft threads (i.e. where
20 the threads overlap its thickness is double that of the threads,
whereas elsewhere it is equal to that of the threads), and
consequently has a more uneven surface. Electroplated woven
fabrics also have this uneven surface, albeit to a lesser
extent. When a woven fabric of this type has been covered with a
25 resist layer, the unevenness of the woven fabric may continue to
make its presence felt in the surface of the resist layer, in
such a manner that more of a relief is formed in the resist
layer. In addition, the high degree of flatness of an
electroformed screen leads to a uniform distance between the
30 dykes of the screen and the surface of the resist layer on the
side of the protective film. The associated advantages are
discussed below in connection with the second aspect of the
invention.

35 In a preferred embodiment of the method according to the
invention, the screen is pressed into the additional resist
layer during step d). As such, the adhesion between the screen
and the additional resist layer is further improved, and/or

established in a shorter time.

Further preferably, the screen is pressed in the additional resist layer under pressure from a roller which makes direct
5 contact with the screen. The use of a roller has the advantage that long and wide sheets of base material can be produced continuously. Moreover, the pressure under which the roller presses the screen into the resist layer, can be controlled and regulated over the whole sheet of base material. Advantageously,
10 opposite of the roller and at the other side of the assembly made up of of screen, resist layer and protective film, a counter-pressure roller is used.

Alternatively, the assembly of protective film and resist layer
15 together with a screen can be pulled by a pulling force over a roller, wherein the side of the protective film is in direct contact with the roller, so that the screen enters into the resist layer without the screen being in direct contact with a roller that exerts a pressure.

20 In the method according to the invention, it is particularly preferable to use a roller of which the pressure-exerting surface is provided with a coating material with an open-cell structure. A method of this type prevents the formation of what
25 are known as dark spots in the base material. Dark spots are formed, for example, when a screen is pressed into a resist layer under pressure from a roller which blocks the openings in the screen during the pressing operation. In this case, the air enclosed in an opening that has been blocked, is compressed. As
30 a result, a pressure difference is produced between an opening which has been blocked by the roller and other openings which have not been blocked, with the result that the quantity of resist which flows into the openings in the base material obtained is not uniform, which is visible in the base material
35 itself. The screen looks darker at the locations where too much resist is present in the openings, hence the name dark spots. The open structure of the coating material prevents the undesirable build-up of pressure, which can give rise to the

formation of dark spots. Examples of suitable coating materials with an open structure are woven mesh, open rubber, foam or open cloth.

- 5 A further preferred embodiment of the method according to the invention makes use of a roller which is in contact with the screen in the tangential direction over a length which is less than the diameter of the openings of the screen at the location of the contact surface of the screen. A method of this type
- 10 further prevents the formation of the dark spots in the base material, since the dimensioning of the roller establishes that it is in fact no longer possible for an opening to be blocked while the screen is being pressed into the resist layer.
- 15 In the method according to the invention, it is preferable to use a roller which is compressible. It is advantageous to use a roller which is only slightly compressible, i.e. slightly deformable, so that the roller can correct any minor unevenness in the contact surface of the screen. The roller advantageously
- 20 comprises a rubber roller made from hard rubber, with a hardness of 70-90 Shore, preferably in combination with a counter-pressure roller with a higher hardness, for example made from metal.
- 25 In a subsequent preferred embodiment of the method according to the invention, a first resist layer is applied with a thickness at least equal to that of the additional resist layer which is applied. For the sake of clarity, it should be noted that where the text refers to the thicknesses of the two resist layers,
- 30 this is to be understood as meaning the thicknesses in the dry state. It has been found that the base material which is produced according to this method has a high degree of smoothness.
- 35 In the method according to the invention, it is preferable to apply an additional resist layer with a thickness of from 2 to 10 micrometres. This type of thickness has in practice proven sufficient to apply the screen to the resist layer. For

practical reasons, the thickness of the first resist layer is advantageously between 5 and 20 micrometres.

Further preferably, in the method according to the invention,
5 the additional resist layer which is applied comprises the same type of resist as the first resist layer which is applied. This has the advantage that one type of resist is sufficient to carry out the method, and that the first and additional resist layers have similar properties in terms of drying rate, viscosity,
10 curing rate, etc.

In a preferred embodiment of the method according to the invention, two intermediate steps are carried out between steps b) and c), namely:

- 15 i) covering the first resist layer with a separating sheet and rolling up the subassembly comprising protective film, first resist layer and separating sheet, and
- ii) then unrolling the rolled-up subassembly and removing the separating sheet.

20 For the sake of clarity, it should be noted that the separating sheet covers that side of the resist layer which is not provided with the protective film. The separating sheet prevents the resist layer from sticking when the protective film to which the
25 dried first resist layer has been applied is being rolled up. If a separating sheet were not present, unrolling presents problems. The cover provided by the separating sheet offers the advantageous option of obtaining a rolled-up subassembly which can be unrolled without problems. This provides the possibility
30 of applying a first resist layer at a certain location while the second resist layer can be applied at another location, preferably directly followed by the application of the screen. Examples of suitable separating sheets include label paper, silicone paper, bleached paper or covering paper.

35 A second aspect of the invention relates to a base material for screen printing, which comprises a protective film, a resist layer comprising photosensitive material, and a screen, the

surface of the resist layer, on the side on which protective film is present, being sufficiently smooth for the Rz value of the said surface to be lower than 15 micrometres. Base materials of this type lead to improved printing results during screen printing, as has already been explained above.

In the base material according to the invention, it is preferable that the distance from the dykes of the screen to the surface of the resist layer on the side of the protective film is uniform. The abovementioned distance is to be understood as meaning the shortest distance between the dykes and the said surface of the resist layer, i.e. measured from the point of a dyke which point has penetrated deepest into the resist layer. The said distance being uniform means that the variation in the distance is slight, preferably less than ± 2 micrometres. Base materials of this type lead to improved printing results during screen printing.

Further preferably, in the base material according to the invention the height of the resist layer is uniform between the dykes of the screen. In this context, the height is to be understood as meaning the distance between the point of a dyke which point has penetrated deepest into the resist layer and the surface of the resist layer between two dykes on the free side of the screen, i.e. the side remote from the protective film. In this context, the term uniform is to be understood as meaning that the variation in depth is slight, preferably less than ± 5 micrometres. Base materials of this type lead to improved printing results during screen printing.

A third aspect of the invention relates to a base material for screen printing, which comprises a protective film, a resist layer comprising photosensitive material, and an electroformed screen. In this case, the base material preferably satisfies the conditions as imposed in accordance with the second aspect of the invention. As has been noted above, the surface of an electroformed screen has a high degree of flatness compared to other screen materials, which has a beneficial influence on the

smoothness of the resist layer on the side of the protective film.

The protective film may be produced from various polymer materials, for example polyethylene, polypropylene, polyester, polyvinyl chloride, polyacrylate, PET, PEI, PBT, PC, etc. The thickness of the film is, for example, between 25 and 500 micrometres.

10 The resist which is used for the resist layer is advantageously a resist based on organic solvents or water. The dry matter content of the resist is preferably between 30 and 60%. The particle size of the resist is preferably less than 25 micrometres, more preferably less than 10 micrometres. The
15 viscosity of the resist is preferably between 1000 and 4000 cP. The resist comprises constituents selected from the group consisting of UV acrylate resin, polyvinyl acetate, polyvinyl alcohol, alkyd, epoxy, melamine, bichromate, diazo compound and water-borne SBQ photopolymer. As has already been noted above,
20 it is advantageous to use the same resist for the first resist layer and the additional resist layer.

Furthermore, it is advantageous for the surface tension of the resist which is applied direct to the film to be less than or
25 equal to the surface tension of the film, in order to achieve a favourable flow of the resist on the film during application of the first resist layer. For this purpose, as an alternative it is also possible to increase the surface tension of the film by a pre-treatment in a corona device.

30

The invention also relates, in a fourth aspect, to a method for producing a base material for screen printing which comprises a screen, a resist layer comprising photosensitive material and a protective film, the method comprising the steps of:

- 35 a) applying the resist layer to one side of the protective film,
b) then applying a screen to the resist layer, the side of the resist layer to which the screen is applied being wet.

Such a method has the advantage that the resist layer is can be

applied in one time, while maintaining the advantages as set out above for the method according to the first aspect.

Preferably, in the above method according to the fourth aspect,
5 the resist layer is dried between steps a) and b), and subsequently the side of the resist layer at which the screen is to be applied is wetted. A step of drying, has the advantage of producing a base material in a shorter time and insures a sufficiently hard, or sufficiently viscous layer into which the
10 screen cannot penetrate.

Advantageously, in the method according to the fourth aspect, measures are applied, analogous to the method according to the first aspect, as set out in claims 3-12, of which measures the
15 advantages are already described above.

The invention will be explained below on the basis of the following example.

20 Example 1

At ambient temperature, a first resist layer is applied by knife and roll coating to a 100 micrometre thick polyester film. The polyester film has an Rz value of between 0.3 and 0.4 micrometre
25 and a surface tension of between 40 and 42 mN/m. The resist has a surface tension of between 35 and 38 mN/m. The resist is a water-borne UV-curing emulsion with a dry matter content of 50% and a viscosity of 3000 cP. The resist comprises as dry matter UV acrylate resin, polyvinyl acetate, polyvinyl alcohol and
30 diazo compound. The particle size of the resist is on average 1.5 micrometre.

The first resist layer is dried at 50°C and has a thickness of 10 micrometres after it has been dried. The dried subassembly
35 made up of polyester film and first resist layer is rolled up, with the resist layer side covered with a separating sheet.

In a subsequent stage, the rolled-up subassembly is unrolled and

an additional resist layer is applied to the first resist layer in a similar manner to that described above for the first resist layer. Immediately afterwards, a screen is applied in the still-wet resist layer using a roller, followed by drying at
5 50°C. The roller is a rubber roll with a hardness of 90 Shore and exerts a pressure of 2 bar. The base material obtained is rolled up with a separating sheet. The thickness of the additional layer is determined afterwards on a dried part to which no screen has been applied, and is 6 micrometres.

10

The invention will also be explained with reference to the appended drawing, in which:

Fig. 1 diagrammatically depicts a cross section through the
15 method according to the invention.

Fig. 1 illustrates a rotatably mounted pressure-exerting roll 1 made from hard rubber (with a hardness of 70-90 Shore), a counter-pressure roll 3 made from metal (with a Shore hardness greater than that of pressure-exerting roll 1). Starting from
20 the right-hand side of the figure, an electroformed screen 5 is supplied from above, comprising a network of dykes 6 which delimit openings 7. At the same time, an assembly comprising a polyester film 10 and a resist layer 13 composed of a first resist layer 15 and an additional resist layer 17 is supplied
25 from the right-hand side, beneath the screen 5. The screen 5 is pressed into the resist layer 13 between the pressure-exerting roll 1 and the counter-pressure roll 3. During this process, the screen 5 penetrates through the additional resist layer 17 and partially into the first resist layer 15. In this way, a base
30 material 25 according to the invention is obtained on the left-hand side of rolls 1 and 3, this base material 25 having the following characteristics. The distance d from the screen to the surface of the resist layer 13 on the side of the protective film 10 is uniform. The distance d , to clarify, is represented
35 as the distance between the surface 18 of the resist layer 13 on the side of the film 10, on the one hand, and the tangent plane 19 of the dykes of the screen 5 on the side which projects into the resist layer 13, on the other hand. The height h of the

- 13 -

resist layer 13 is also uniform between the dykes 6. For clarity, the height h is represented as the distance between the tangent plane 19 of the dykes of the screen and the surface of the resist layer 13 between two dykes 6 on that side of the base material 25 where the screen 5 projects out of the resist layer 13.

CLAIMS

1. Method for producing a base material (25) for screen
5 printing, which comprises a screen (5), a resist layer (13)
comprising photosensitive material and a protective film
(10), the method comprising the steps of:
 - a) applying a first resist layer (15) to one side of the
protective film (10),
 - 10 b) drying the first resist layer (15),
 - c) applying an additional resist layer (17) to the first
resist layer (15), and
 - d) then applying a screen (5) to the additional resist layer
15 (17), the side of the additional resist layer (17) to which
the screen (5) is applied being wet, and in which the
resist layer (13) comprises the additional resist layer
(17) and the first resist layer (15).
2. Method according to claim 1, in which the screen (5) is
20 applied without the additional resist layer (17) being
dried beforehand.
3. Method according to one of the preceding claims, in which
the screen (5) which is applied is an electroformed screen.
25
4. Method according to one of the preceding claims, in which
the screen (5) is pressed into the additional resist layer
(17) during step d).
- 30 5. Method according to claim 4, in which the screen (5) is
pressed into the additional resist layer (17) during step
d), under pressure from a roller (1) which makes direct
contact with the screen (5).
- 35 6. Method according to claim 1, in which the pressure-exerting
surface of the roller (1) is provided with a coating
material with an open-cell structure.

7. Method according to one of the preceding claims 5 or 6, in which the roller (1) makes direct contact with the screen (5) in the tangential direction over a length which is less than the diameter of the openings of the screen (5) at the contact surface of the screen.
8. Method according to one of the preceding claims 5-7, in which the roller (1) is compressible.
9. Method according to one of the preceding claims, in which the first resist layer (15) which is applied has a thickness at least equal to that of the additional resist layer (17) which is applied.
10. Method according to one of the preceding claims, in which the additional resist layer (17) which is applied is from 2 to 10 micrometres thick.
11. Method according to one of the preceding claims, in which the additional resist layer (17) which is applied comprises the same type of resist as the first resist layer (15) which is applied.
12. Method according to one of the preceding claims, in which two intermediate steps are carried out between steps b) and c), namely:
 - i) covering the first resist layer (15) with a separating sheet and rolling up the subassembly comprising protective film (10), first resist layer (15) and separating sheet, and
 - ii) then unrolling the rolled-up subassembly and removing the separating sheet.
13. Base material (25) for screen printing, which comprises a screen (5), a resist layer (13) comprising photosensitive material and a protective film (10), the screen (5) comprising a network of dykes which delimit openings, characterized in that the surface of the resist layer (13),

on the side on which protective film (10) is present, is sufficiently smooth for the Rz value of the said surface to be lower than 15 micrometres.

- 5 14. Base material (25) for screen printing according to claim 13, characterized in that the distance (d) from the dykes (6) of the screen (5) to the surface of the resist layer (13) on the side of the protective film (10) is uniform.
- 10 15. Base material (25) for screen printing according to claim 13 or 14, characterized in that the height (h) of the resist layer (13) is uniform between the dykes (6) of the screen (5).
- 15 16. Base material (25) for screen printing, which comprises an electroformed screen (5), a resist layer (13) of photosensitive material and a protective film (10), in particular according to claim 13, 14 or 15.
- 20 17. Method for producing a base material (25) for screen printing which comprises a screen (5), a resist layer (13) comprising photosensitive material and a protective film (10), the method comprising the steps of:
- 25 a) applying the resist layer (13) to one side of the protective film (10),
- b) then applying a screen (5) to the resist layer (13), the side of the resist layer (13) to which the screen (5) is applied being wet.
- 30 18. Method according to claim 17, wherein the resist layer (13) is dried between steps a) and b), and subsequently the side of the resist layer (13) at which the screen (5) is to be applied is wetted.

ABSTRACT

Method for producing a base material (25) for screen printing, which comprises a protective film (10), a screen (5) and an intermediate resist layer (13) comprising photosensitive material, the method comprising the steps of applying a first resist layer (15) to one side of the protective film (10), drying the first resist layer (15), applying an additional resist layer (17) to the first resist layer (15), and then applying a screen (5) to the additional resist layer (17), with that side of the additional resist layer (17) to which the screen (5) is applied being wet. The invention also describes a base material (25) for screen printing, which comprises a protective film (10), an electroformed screen (5) and an intermediate resist layer (13) comprising photosensitive material.

Fig. 1